



**MIRROR BLANK MATERIAL, ALIGO MODE CLEANER
MIRROR #3**

AUTHOR:	CHECKED:	DATE	APPROVALS		
			DCN NO.	REV	DATE
R. Martin, D. Reitze		04-02-07			

Applicable Documents

D070085-00-D ALIGO Mode Cleaner Mirror #3 Blank
MIL-G-174-B Glass, Optical

Requirements

Physical Dimensions	Per D070085-00-D ALIGO Mode Cleaner Mirror #3 Blank
Diameter	153 mm, +1 mm, -0 mm
Thickness	81 mm, +1 mm, -0 mm
Clear Aperture	Central 140 mm
Serial Number	Blanks shall be serialized as MC3-XX, where XX increments starting at 01
Material	Fused Silica, Grade 0C
Final Shaping	Shaping shall be performed using a progression of grit size ending with a 320 or smaller grit wheel
Defect Depth	Maximum on any surface or corner is less than 0.5 mm
Homogeneity	$\leq 5 \times 10^{-7}$ peak to valley at $\lambda = 632.8$ nm, within the central 140 mm
Birefringence	≤ 2 nm/cm within the central 140 mm
Bubble and inclusion cross section within clear aperture	Total ≤ 0.03 mm ² /100 cm ³ of glass Inclusions with a diameter of 0.06 mm or less are disregarded Maximum inclusion diameter ≤ 0.1 mm No inclusions within clear aperture of center 100 mm
Striae within the clear aperture	Grade A according to MIL-G-174
Absorption	< 10 ppm per centimeter at $\lambda=1.06$ μ m



MIRROR BLANK MATERIAL, ALIGO MODE CLEANER MIRROR #3

Table 1: Measurement Matrix - Frequency and Method

Specification	Test Method	Frequency of Inspection	Data Delivered
Physical Dimensions	Visual Inspection	100%	Diameter, Thickness
Serial Number	Visual Inspection	100%	Inspection Report included with Certification
Material	Process Control Material Certification	100%	Certification
Defect Depth	Visual Inspection	100%	Certification
Homogeneity	Interferometric Measurement	100%	Phase Map
Birefringence	MIL-G-174, Section 4.4.5	100%	Inspection Report included with Certification
Inclusions	Visual Inspections	100%	Hand sketch indicating location and dimensions
Striae	MIL-G-174, Section 4.4.5, method 1 or 2 (in optical axis only)	100%	Inspection Report included with Certification
Absorption at 1.06 μm	Material Certification	100%	Certification