



Statement of Work Fabrication Maraging Steel Blade Springs for Advanced LIGO BSC-ISI

The following documents are incorporated into and made a part this Statement of Work (SOW). Click on the following LIGO Document Control Center (DCC) links to access these documents or go on line to the LIGO Public DCC at <https://dcc.ligo.org/> to access the DCC#.

1.0 Terms:

| <u>DCC #</u> | <u>Description</u> |
|-----------------------------|---|
| C080185-v1 | Laser Interferometer Gravitational Wave Observatory (LIGO) Commercial Items or Services Contract General Provisions California Institute of Technology “Institute”, LIGO Rev 11/12/08 |
| F0810001-v4 | Technical Direction Memorandum. |

2.0 Quality Control:

| <u>DCC #</u> | <u>Description</u> |
|---|---|
| Q0900001-v4 | Advanced LIGO Supplier Quality Requirements, dated 2/10/10, describes following contractor/supplier QA/QC actions for this procurement: |
| <input type="checkbox"/> 3.1 Pre-Award Inspection | <input checked="" type="checkbox"/> 3.9 Discrepant Material Storage |
| <input checked="" type="checkbox"/> 3.2 Supplier In Process Quality Control | <input checked="" type="checkbox"/> 3.10 Quality Records |
| <input checked="" type="checkbox"/> 3.3 In Process Inspection | <input type="checkbox"/> 3.11 Drawing and Specification Change Control |
| <input checked="" type="checkbox"/> 3.4 Pre-Ship Inspection | <input type="checkbox"/> 3.12 Welding Certification |
| <input checked="" type="checkbox"/> 3.5 Receiving Inspection | <input checked="" type="checkbox"/> 3.13 End Item Data Package (including Certifications of Compliance) |
| <input checked="" type="checkbox"/> 3.6 Discrepant Material | <input type="checkbox"/> 4.1 Design Verification |
| <input checked="" type="checkbox"/> 3.7 Material Review Action | <input type="checkbox"/> 4.2 Raw Material Procurement |
| <input checked="" type="checkbox"/> 3.8 Material Review Actions at Contractor | <input checked="" type="checkbox"/> 4.3 Traceability of Materials |
| | <input checked="" type="checkbox"/> 4.4 Calibration Program |
| | <input type="checkbox"/> 4.5 Critical Interface |
| | <input checked="" type="checkbox"/> 4.6 Cleanliness |
| | <input checked="" type="checkbox"/> 4.7 Packaging |
| | <input checked="" type="checkbox"/> 4.8 Storage |
| | <input checked="" type="checkbox"/> 4.9 Transport |
| | <input type="checkbox"/> 4.10 Customs |

For the above list the Supplier shall: 1) Identify the corresponding sections/paragraphs in their existing QA/QC system 2) meet or exceed the design requirements contained in the attached engineering documents for each area called out.

3.0 End Item Data Package:

At the time of delivery of the parts, the Supplier shall also provide the following data, as a minimum:

- Any as-built modifications (with approval of the LIGO Contracting Officer) as mark-ups to the drawings
- Certification that the material used is the material provided by LIGO
- Dimensional & QC inspection reports—this shall include a report showing that parts have been inspected and fall within specified tolerances.
- Certificate or statement of compliance with all contract and drawing process restrictions.
- Heat treatment certification
- Material hardness measurements

4.0 Included Documents:

The drawings cited below are only partially dimensioned. In addition to the drawings, the contractor will be provided with CAD solid models of the parts (SolidWorks Professional 2009, SP5.0)

| <u>DCC #</u> | <u>Description</u> |
|-----------------------------|--|
| D0901541-v1 | Blade Spring, stage 0-1 |
| D0902502-v1 | Blade Spring, stage 1-2 |
| E0900023-v9 | Manufacturing Process for Cantilever Spring Blades for Advanced LIGO |
| E0900364-v2 | Metal components intended for use in the AdvLIGO Vacuum System |

5.0 Scope:

This SOW is for the fabrication of two (2) unique parts detailed in the two (2) unique drawings linked in this package. These parts are made from maraging steel. Note that these springs will NOT be nickel plated despite references to nickel plating in the linked document E0900023-v9. These parts will be used in the vacuum system as part of the BSC ISI system for Advanced LIGO.

6.0 Quantity Required:

| | | |
|-------------|-------------------------|----|
| D0901541-v1 | Blade spring, stage 0-1 | 45 |
| D0902502-v1 | Blade spring, stage 1-2 | 45 |

7.0 Delivery Requirements: (Actual delivery schedule is located in RFQ or RFP)

The deliveries are FOB at these destinations, i.e. the contractor has responsibility for shipping title and control of goods until they are delivered and the transportation has been completed. The contractor selects the carrier and is responsible for the risk of transportation and for filing claims for loss or damage.

Shipping Locations - These items will be shipped to:

MIT LIGO (MIT)
c/o Myron MacInnis
NW-17
175 Albany St
Cambridge MA 02139

and

LIGO Livingston Observatory (LLO)
Attn: Joe Hanson and Tom Gentry
19100 LIGO Lane
Livingston, LA 70754

and

LIGO Hanford Observatory (LHO)
Attn: Hugh Radkins and Jodi Fauver
127124 North Route 10
Richland, WA 99354

Shipping Containers:

The contractor is responsible for providing shipping containers and transportation which protects these parts from damage from the transportation environment (weather, handling, accidents, etc.). Mating edges of parts should be especially protected from damage during shipping.

8.0 Manufacturing:

8.1 Precedence

The Statement of Work (SOW) sections below regarding processing or fabrication of the parts are meant to convey the scope and nature of the requested work. If there is a conflict between the SOW and the drawing, the drawing has precedence.

The parts are to be produced using the CAD models which will be provided to the contractor upon award. If there are discrepancies between the drawings and the CAD model, the model takes precedence.

The order of the manufacturing process sequence is important. The order of the sequence is as listed below.

8.2 Restrictions

- Machine all surfaces to remove oxides and mill finish. Abrasive removal techniques are not acceptable.
- All machining fluids must be fully synthetic, water soluble (not simply water miscible) and free of sulfur, chlorine, and silicone.
- Thoroughly clean part to remove all oil, grease, dirt, and chips with soap and water. Follow with solvent (acetone) wipe. Pay close attention to holes.

8.3 Materials

Material: Start with maraging 300 (MIL-S-46850D), solution annealed. Intermediate machining and strain relief steps are acceptable.

The maraging steel material for the two blade spring types will be supplied by LIGO. The size of the billets for part D0901541 will be:

width: 9.00" +.500, -0.0, length: 22.65" +.750, -0.0, depth: 0.88" +.250, -0.0 (one billet per spring)

and for part D0902502 will be:

width: 6.88" +.500, -0.0, length: 18.50" +.750, -0.0, depth: 0.75" +.250, -0.0 (one billet per spring)

It will be in the annealed condition.

The maraging steel will arrive as billets in the two sizes listed above, labeled in sets of three. These sets must be kept together throughout the manufacturing process (THIS IS CRUCIAL) and marked per section "8.11 Marking" below.

Also refer to section 2.1 of LIGO E0900023-v9.

All materials specified by drawings or SOW have been approved for use in the UHV environment in LIGO. No materials may be substituted or added without prior knowledge and testing by LIGO. Cast tooling plate is not permitted.

8.4 Machining

Note: All dimensions apply after heat treatment, section 2.8 of LIGO E0900023-v9. (Note that for the purposes of document LIGO E0900023-v9, the springs in this SOW are "thick" and "flat".) It is required that the spring blades be roughed cut oversize, followed by the heat treat process described in E0900023-v9. Final machining is then required to finish dimensions. This will be necessary to remove distortions that may occur during the heat treatment.

All parts are to be machined. No grinding or lapping with abrasive wheels, cloth or stones is permitted. No sanding of any type. No parts shall be cast or molded. Water soluble (not just water miscible) cutting fluid (lubrication) is to be used for all machining operations. The use of cutting fluids or lubricants, which contain sulfur, chlorine or silicone compounds is prohibited.

Please refer to sections 2.2 and 2.4 of LIGO E0900023-v9.

8.5 Heat Treatment

Please refer to sections 2.7 and 2.7.2 of LIGO E0900023-v9.

8.6 Post Heat Treatment Machining

Please refer to section 8.4 above. All drawing dimensions apply post heat treatment

8.7 Finishing

Any required surface finish is defined in the drawings. Localized scratches, digs and blemishes should be minimized.

8.8 Marking

Marking location is shown on the drawings.

All parts must be marked with a part number, revision code and serial number at the location indicated on the drawing. Marking is to be accomplished by mechanically scribing, stamping or engraving (no dyes or inks).

If not indicated in the drawing, mechanically scribe, stamp or engrave as follows:

<drawing number> - <revision code>, <type number if applicable>

<unique 3 digit serial number starting at 001 for the first part and incrementing thereafter>

As an example:

D0900026-v1

NOTE: Each three successive serial numbers will have been taken from the same set of maraging billets, e.g. 001, 002, 003 from one set; 004, 005, 006 from one set, etc. See section 8.3 above.

Also where indicated, mechanically scribe, stamp, or engrave (no dyes or inks) any LABELS shown on drawing sheets.