

JPL ANALYTICAL CHEMISTRY LABORATORY
Analytical Chemistry and Materials Development Group 3531
Propulsion and Materials Section 3530

To: Hugh Radkins **04-07-10**

From: Mark Anderson and Jerami Mennella

Subject: LHO LABO – HR202 (received on 04-05-10) **revised 2**

Purpose

The purpose is to determine the level and identity of molecular (oily) contamination.

Method

LVR Analysis

The low volatility residue (LVR) was analyzed using Diffuse Reflectance Infrared Fourier Transform (DRIFT) spectroscopy (1). Blank samples were run along with the samples (2). FTIR provides chemical functional group information for quantitative analysis and qualitative identification of materials. The analysis followed the JPL ACL-120 procedure that complies with IEST-STD-CC1246D (3) and is sensitive to stringent levels (4).

Results

Sample	Chemical Functional Group	Amount ($\mu\text{g}/\text{cm}^2$)
2 D071050, 004, HAM ISI Optical Table, 36 holes	AHC	~ 0.02*
3 D071050, 004, HAM ISI Optical Table, 36 holes	AHC	0.2*
4 D071050, 004, HAM ISI Optical Table, Surface Areas	AHC	≤ 0.02
5 D071050, 004, HAM ISI Optical Table, Surface Areas	AHC	0.03

*Based on a calculated area of 171.5 cm²

Terminology:

AHC: Aliphatic hydrocarbon, base oil of common lubricants
 Esters: common sources are from plasticizers and fingerprints

$\mu\text{g}/\text{cm}^2$: micrograms per square centimeter

LIGO-E1000102-v2

References and Notes

1. M. S. Anderson et al "Analysis of Semi-Volatile Residues Using Diffuse Reflectance Infrared Fourier Transform Spectroscopy" in *Optical System Contamination: Effects, Measurements, and Control VII*; July 2002, edited by Phillip T. C. Chen and O. Manuel Lee; Proceedings of the SPIE, Vol. 4774, pp. 251-261, (2002).

2. The wipe blanks are less than 10% the amount in the sample and this is subtracted from the reported sample amount. High blanks (greater than 10% of the sample) are noted in the report. A typical solvent wipe has a detection limit of $\sim 0.005 \mu\text{g}/\text{cm}^2$ of removed residue from a 100cm^2 sample. Note this limit is well below the adventitious carbon level (ref. 4). Lower limits are possible using modified methods.

3. The analysis conforms to the Institute of Environmental Science and Technology (IEST), Contamination Control Division Document IEST 1246D "Product Cleanliness Levels and Contamination Control Program". The contamination limits are generally set by Contamination Control Engineering. At typical limit is "Level A" (IEST-STD-CC1246D) and this is 1 microgram per square centimeter ($\mu\text{g}/\text{cm}^2$) and this corresponds to an average film thickness of 100 angstroms (assuming a density of 1.0). In many cases more stringent limits apply (4).

4. Very clean surfaces, $\leq 0.02 \mu\text{g}/\text{cm}^2$, with mono-molecular layers or less are more complex to describe when cleaning or analyzing. Carbon/hydrocarbon based substances are known to rapidly (within ~ 1 hour) accumulate on most, if not all, freshly exposed surfaces. This "adventitious" carbon is well documented in clean rooms and vacuum systems and compositionally varies by environment. Adventitious carbon is a discontinuous layer of approximately ~ 0.2 nanometers thick or $\sim 0.02 \mu\text{g}/\text{cm}^2$ up to $0.1 \mu\text{g}/\text{cm}^2$ (for $\rho = 1$). The last mono-layer fractions may in some cases be strongly adsorbed to the surface as a "corrosion" layer. Therefore solvent based sampling methods may not remove these fractions, particularly if the surface is porous. When specifying cleanliness level to less than A/10 IEST-STD-CC1246D ($0.1 \mu\text{g}/\text{cm}^2$) these monolayer effects become more significant. See also: H. Piao and N. S. McIntyre, "Adventitious carbon growth on aluminum and gold-aluminum alloy surfaces", *Surface and Interface Analysis*, 2002; 33: 591–594.