



SPECIFICATION

aLIGO ISC Optics:

1" High Reflectors @ 1064nm

APPROVALS	DATE	RE V	DCN NO.	BY	CHECK	DCC	DATE
AUTHOR: L. BARSOTTI	10-14-10						
CHECKED:							
APPROVED: P.FRITSCHEL							
DCC RELEASE							

1 Description

1" Ø Flat/Flat high reflector @ 1064nm

2 Material

Corning HPFS 7980 (high purity fused silica, UV grade)  
Grade 0A (Low inclusion class: <0.3 mm<sup>2</sup> cross section, 0.1 mm max. size;  
Homogeneity < 1ppm)

3 Dimensions

1"Ø +.000/-.005" X .250" ± .020" tk., Plano / Plano

4 Surface Roughness

Side 1

Super polish  
Surface Roughness: <1Å RMS in CA  
Surface Quality: 10-5

Side 2

Commercial Polish  
Surface Roughness: <5Å RMS in CA  
Surface Quality: 20-10

5 Surface Figure

Side 1

Flat < λ/10 at 632.8 over central 80%

Side 2

Flat < λ/10 at 632.8 over central 80%



## SPECIFICATION

**aLIGO ISC Optics:****1" High Reflectors @ 1064nm****6 Coating**

Wavelength: **1064nm**

Angle of incidence:  $45^{\circ} \pm 5^{\circ}$  (best effort for wider AOI range)

**Side 1**

R  $\geq$  99.995% @ 1064nm (best effort) for **s** and **p**-polarization

**Side 2**

AR coating, R < 1% @ 1064nm (best effort) for **s** and **p**-polarization

Serial numbers and registration marks shall be scribed or etched on the barrel of the optic for in-vacuum use

**Coating vendor to provide:**

1. Three spectrophotometer graphs of the reflectance and transmittance of the HR coatings; one covering the spectrum from 500nm to 1200nm; the others, with increased sensitivity, showing wavelengths from 900nm to 1100nm and from 500nm to 600nm
2. Spectrophotometer graphs of the reflectance of the AR coating taken as cited above.