



SPECIFICATION

Shape and polish LASTI ETM blank

AUTHOR:	CHECKED:	DATE	APPROVALS		
			DCN NO.	REV	DATE
G. Billingsley	Coyne	6-16-06	E060179-00	A	

Applicable Documents

- [LIGO-D040431-B](#) Quad ETM Silica Test Mass
- [LIGO-D030265-A](#) Fused Silica Blank LASTI Test Mass
- [LIGO-E030309-A](#) Fused Silica Blank, LASTI Test Mass, R&D

Requirements

Physical Configuration

- Shape and Polish only according to
- LIGO-D040431-B Quad ETM Silica Test Mass, X-dimension 200.6 ± 0.2 mm
- Fabricate from
- LIGO-E030309-A Fused Silica Blank, LASTI Test Mass, R&D
- LIGO-D030265-A Fused Silica Blank LASTI Test Mass

Registration Marks

Registration marks shall be etched, ground or sandblasted and located per LIGO-D040431

Serial Number

Serial Number "LEM 1" shall be etched, ground or sandblasted and located per LIGO-D040431

Side and Bevel Polish

Sides and Bevels shall be polished using a progression of smaller grit sizes. The last step before final polish shall be equal to or less than a five micrometer grit finish. These surfaces shall appear transparent with no grey, scuffs or scratches visible to the naked eye when viewed in normal room light against a black background.

Surface 1 and 2 as defined in LIGO-D040431

Surfaces 1 and 2 be polished using a progression of smaller grit sizes. The last step before final polish shall be equal to or less than a 15 micrometer grit finish.



SPECIFICATION

Shape and polish LASTI ETM blank

Mounting Flat Figure, measured over the Bond Area per D040431, 2 places

Flat: Peak to valley maximum deviation over the bond area, with tilt subtracted: < 60 nm
 Surface rms error over the bond area: < 10 nm

Inspections

Specification	Test Method	Data Delivered
Outside Diameter	Physical inspection	Measured dimension
Wedge	Physical inspection	Measured dimension
Thickness	Physical inspection	Measured X- dimension per D040431-A
Bond area flatness	Interferometry	Surface map for each bond area