



COMPONENT SPECIFICATION

TITLE
SUBSTRATE, INPUT TEST MASS

APPROVALS:	DATE	REV	DCN NO	BY	CHK	DCC	DATE
DRAWN:			E980005-00-D				1-22-98
CHECKED:							
APPROVED:							
DCC RELEASE:							

Applicable Documents

- LIGO-D960787-B-D Input Test Mass Substrate, 4K
- LIGO-D960803-B-D Input Test Mass Substrate, 2K
- LIGO-E960095-A-D Mirror Blank Material, Input Test Mass
- LIGO-D960794-A-D Core Optic Blank

Requirements

Physical Configuration

- According to
 - LIGO-D960787 Input Test Mass Substrate, 4K
 - LIGO-D960803 Input Test Mass Substrate, 2K
- Fabricate from
 - LIGO-E960095 Mirror Blank Material, Input Test Mass

Serial Number

The Serial number shall be of the format:
 XITMYZ Where
 X is 2 or 4 according to the interferometer length named in the Drawing Title
 YY is incremental for each optic starting at 01.
 Z is the current revision letter of this Specification

Registration Mark

Registration mark shall be etched, ground or sandblasted coincident with the registration mark drawn on the Blank within 5 mm. The arrow orientation used on the Blank will be preserved if possible or changes reported in detail. Reference LIGO-D960794, Core Optic Blank.

Side and Bevel Polish

Sides and Bevels shall be polished from a five micrometer grit finish. These surfaces shall appear transparent with no grey, scuffs or scratches visible to the naked eye when viewed in normal room light against a black background.



COMPONENT SPECIFICATION

TITLE

SUBSTRATE, INPUT TEST MASS

Scratches and Point defects

Point defects of radius greater than 25 micrometers are treated like scratches for the purpose of this specification. Point defects of radius less than 2.5 micrometers are disregarded.

Scratches, Side 1

The total area of scratches within the central 80 mm diameter shall not exceed 25×10^3 square micrometers (width times length.)

The total area of scratches outside the central 80 mm diameter shall not exceed 250×10^3 square micrometers.

Scratches, Side 2

The total area of scratches within the central 80 mm diameter shall not exceed 75×10^3 square micrometers (width times length.)

The total area of scratches outside the central 80 mm diameter shall not exceed 750×10^3 square micrometers.

Point Defects, Side 1

There shall be no more than 10 point defects within the central 80 mm diameter

There shall be no more than 100 point defects on the entire surface

Point Defects, Side 2

There shall be no more than 30 point defects within the central 80 mm diameter

There shall be no more than 100 point defects on the entire surface

Inspection Method

1. The surface is examined visually by two observers independently. The examination is done against a dark background using a three-bundle fiberoptic illumination system of 200 W total power. A 100% inspection of the surface is carried out. Pits and scratches down to 2 micrometers in width can be detected using this method of inspection. Any scratches that are detected will be measured using a calibrated eyepiece.
2. Further inspection will be done with a 6X eyeglass using the same illumination conditions, again with two observers. Sleeks down to 0.5 micrometers wide can be detected using this method. The surface will be scanned along one or two chords from centre to edge, then at ten positions around the edge, and ten to fifteen positions near the centre.
3. An inspection is then carried out with a dark field microscope with a similar sampling frequency as described in section 2.



COMPONENT SPECIFICATION

TITLE

SUBSTRATE, INPUT TEST MASS

Surface Figure, measured over the central 200 mm diameter

All specified quantities refer to the physical surface of the optic.

Surface 1: Spherical, concave.

Radius of curvature: 14,180 meters +140 meters, -1000 meters

Astigmatism: < 13 nanometers (surface peak to valley)

Surface 2: Nominally flat.

Measured at 690 nm with the wavefront transmitted through Side 2, passing through the material, reflected from Side 1 back along the same path.

Radius of curvature of the wavefront: 9,740 meters +500 meters, -100 meters

Astigmatism: < 15 nanometers (surface peak to valley)

Surface Errors

All specified quantities refer to the physical surface of the optic.

The following root mean square standard deviation (σ_{rms}) values are calculated from the phase maps which are to be provided with each optic. σ_{rms} is defined as the square root of the mean of the square of each pixel value. Known bad pixels are excluded from this calculation.

Surface 1, Low Spatial Frequency Band: $\leq 4.3 \text{ cm}^{-1}$

With piston, tip, tilt, power (best fit spherical surface) and astigmatism removed over the central 200 mm diameter aperture:

$\sigma_{\text{rms}} < 1.6$ nanometers

With piston, tip, tilt, power (best fit spherical surface) and astigmatism removed over the central 80 mm diameter aperture:

$\sigma_{\text{rms}} < 0.8$ nanometers

Surface 2, Low Spatial Frequency Band: $\leq 4.3 \text{ cm}^{-1}$

With piston, tip, tilt, power (best fit spherical surface) and astigmatism removed over the central 200 mm diameter aperture:

$\sigma_{\text{rms}} < 3.2$ nanometers

With piston, tip, tilt, power (best fit spherical surface) and astigmatism removed over the central 80 mm diameter aperture:

$\sigma_{\text{rms}} < 1.6$ nanometers

Surface 1 and Surface 2, High Spatial Frequency Band: $4.3 - 7,500 \text{ cm}^{-1}$

$\sigma_{\text{rms}} < 0.2$ nanometers, Measured at the following locations:

1. The center of the mirror substrate.
2. Four positions equally spaced along the circumference of a centered, 80 mm diameter circle.
3. Three positions equally spaced along the circumference of a centered, 200 mm diameter circle.



COMPONENT SPECIFICATION

TITLE

SUBSTRATE, INPUT TEST MASS

Specification	Test Method	Frequency of Inspection	Data Delivered
Physical Dimensions	Visual Inspection	100%	Diameter, Thickness, Bevel dimension, Wedge angle.
Side and Bevel Polish	Visual Inspection	100%	Inspection Report included with Certification
Scratches and Point defects	Visual Inspection	100%	Hand sketch including scratch/pit dimensions
Registration Mark Location/Orientation	Visual Inspection	100%	Inspection Report included with Certification
Registration Mark Dimensions	Visual Inspection	100%	Inspection Report included with Certification
Identification Location	Visual Inspection	100%	Inspection Report included with Certification
Identification Serial number	Visual Inspection	100%	Inspection Report included with Certification
Surface Figure	Interferometry	100%	Surface Map
Surface Errors - Low Spatial Frequency	Interferometry	100%	Surface Map
Surface Errors - High Spatial Frequency	High resolution Surface Map	100%	Surface maps for 3 central locations. Numerical values included with Certification

Data:

Orientation: For the purpose of all data collection the Registration mark shall be at the top center of the optic.

Format: All Data shall be delivered according to Table 1. In addition to the hard copy the Surface Data shall be delivered on IBM PC compatible disk in ASCII format. Phase difference data shall be in units of nanometers.