



PROCESS SPECIFICATION

TITLE

Small Optics Cleaning Procedures

APPROVALS:	DATE	REV	DCN NO	BY	CHK	DCC	DATE
DRAWN: H. Armandula	05-10-99	B	E990206-00-D	H.A			
CHECKED: D. Cook							
APPROVED: D. Coyne							
DCC RELEASE:							

Small Optics Cleaning Procedures

Equipment, Tools and Materials

Class 100 laminar flow bench / sink
 Deionized water, 18 Megohms, filtered (0.2 micron filter) at point of use.
 Dry nitrogen cylinder, 99.99% pure
 Ionizing blow-off gun with 0.2 micron filter.
 Berkshire Fastisorb 820 tissue
 Berkshire Lenx 90 tissue
 Crystallizing dish for washing (150mm. dia.x 75mm. ht.)
 Clean, storage mirror holders.
 (Holders should be cleaned with Liquinox solution and thoroughly rinsed under DI water, pat dry with Fastisorb 820 wipes and blown dry using ionizing gun and dry nitrogen.)
 Hot plate
 Gloves - Ansell Edmont Latex 90-576
 Liquinox solution prepared as follows:
 To 2 liters of filtered DI water; add 40 ml. of Liquinox detergent.
 Place beaker on a hot plate.
 While stirring the solution, increase temperature to 70 degrees C; once the temperature is reached, keep stirring for at least 15 minutes.
 Remove from hot plate - Solution is ready to use.
 Life shelf of the solution is one week while covered.

Washing and Drying - Coated surfaces 1 and 2 -

Cleaning steps 1 thorough 15 are formulated to remove heavy contamination from the optics and applies to optics without magnet assemblies.

All procedures listed under these Cleaning Procedures must be performed under a Class 100 laminar flow bench, while suited-up in clean room garments including, but not limited to: coat, booties, bonnet, gloves, facial mask. This applies to anyone handling or near any optics being cleaned.

1. Line the bottom of the Pyrex dish with 3-4 sheets of Lenx 90 tissue cut to size. Place the mirrors to be cleaned in the dish.
2. Cover with Liquinox solution ensuring that the mirrors are completely immersed.
3. Warm the solution to 70 degrees C.



PROCESS SPECIFICATION

TITLE

Small Optics Cleaning Procedures

4. Soak the immersed parts, keeping the dish on the hot plate, for 15 min. at 70 degrees C.
5. Bring the temperature down to 40 degrees C.
6. Remove the mirror from the dish and immediately place under running DI water.
- Never allow any surface wetted with Liquinox to get dry!!!!**
7. With a soft lens tissue (Lensx 90), wetted with the detergent solution, wipe the edges of the optic. Discard the tissue.
8. Repeat the procedure wiping the bevels of both surfaces. Discard tissue.
9. Clean both coated surfaces under running DI water, utilizing a soft lens tissue wetted with Liquinox and scrubbing with smooth, soft strokes.
10. Rinse the parts under running DI water while scrubbing gently (smooth and soft strokes) with a fresh lens tissue
11. Final rinse, spraying only deionized water over the entire part for at **least** 10 seconds. Stop DI water flow. NOTE: If the water does not sheet off the mirror surface at this time, repeat steps 4 through 11.
12. Place the mirror, resting on its edge over several sheets of Lenx 90 tissue.
13. With the ionizing gun, utilizing pure, dry nitrogen and low pressure (45/50 lbs / in.²), slowly blow the edges of the mirror and the coated surfaces starting from the top and working towards the bottom. Ensure that no water remains on the surfaces.
14. Inspect the mirror surfaces for streaks or water marks in a dark room, over a dark background, with a high intensity light.
15. Place the cleaned mirrors in their appropriate storage holders. Keep in a clean area until ready to use.

To clean mirrors with magnet assemblies:

16. Wet the mirror surfaces with DI water.
17. Wet a Lenx 90 tissue with warm (70 degrees C) Liquinox solution.
18. Gently and thoroughly scrub both surfaces of the mirror with the tissue, exercising caution when wiping around the magnets.
19. Rinse under running DI water scrubbing softly the surfaces with a fresh tissue.
20. Final rinse by spraying only DI water over the entire mirror for at least 10 seconds. Stop the water flow.
21. Place the mirror, resting on its edge over several sheets of Lenx 90 tissue.
22. With the ionizing gun, utilizing pure, dry nitrogen, slowly blow the sides of the mirror and the coated surfaces starting from the top. Blow on the magnets from top to bottom to ensure that they are well dry.
23. Continue blowing downwards ensuring that the bottom magnets are dry. Be sure that no water remains on the surfaces.
24. If needed wipe edges with alcohol.
25. Inspect the mirror surfaces for streaks or water marks in a dark room, over a dark background, with a high intensity light.
26. Place the cleaned mirrors in the appropriate storage until ready to balance.