

Scaling up coating Brownian noise measurements

M. Abernathy

July 17, 2015

1 Intro

The purpose of this document is to calculate levels of coating Brownian thermal noise given laboratory direct measurements at smaller scales. We will do this by applying some scaling rules derived from coating Brownian noise theory. By the end of this document, we should have calculated the level of coating Brownian thermal noise expected in the aLIGO interferometers if they were coated with the same coatings as measured in the TNI [1, 2, 3] and in the Caltech rigid cavity measurement (TNC) [4, 5], but with a film thickness scaled to be comparable with the HR films on the ETMs and ITMs in aLIGO. We can then use these values to compare with the noise levels seen in the aLIGO interferometers to determine if they have reached coating thermal noise limitations.

2 Lab Measurements

2.1 TNI

The bulk of the information on the TNI can be found in reference [1]. However, I had to dig up the mirror dimensions from the DCC [6]. The mirrors are 4" in diameter and 4" in height. The beam waist, w_0 , was about 160 *um* for all measurements. Four coatings were measured in the TNI:

1. Quarter-wave stack: silica/tantala
2. Thermal noise optimized stack: silica/tantala
3. Quarter-wave stack: silica/Ti:tantala
4. Thermal noise optimized dichromic stack: silica/Ti:tantala.

These are listed as TNI(1-4) in table 1. All are on silica substrates

The values for $S_x(100\text{Hz})$ were calculated by taking the values for ϕ_{SiO_2} , $\phi_{Ta_2O_5}$, and $\phi_{TiO_2:Ta_2O_5}$ given in tables IV and V of [1], and plugging them back into equations (1) and (2) of that same paper. This should give a good approximation of the actual value of S_x they would have measured.

Optic	w_0 [μm]	a [cm]	d [μm]	H [cm]	$S_x(100\text{Hz})$ [$\text{m}^2 \text{Hz}^{-1}$]
TNI(1)	160	5.08	4.55	10.16	1.06e-35
TNI(2)	160	5.08	5.41	10.16	8.82e-36
TNI(3)	160	5.08	4.21	10.16	7.79e-36
TNI(4)	160	5.08	3.81	10.16	6.84e-36
TNC	182	1.27	4.53	0.635	1.1e-35
ITM	53000	17	2.8	20	–
ETM	62000	17	5.9	20	–

Table 1: Values useful for converting coating Brownian noise. TNI(1-4) refers to the four different coatings measured in the Thermal Noise Interferometer at Caltech [1, 2, 3]. TNC refers to the reference cavity measurements made at Caltech by Tara Chalermongsak [4, 5]. Values for ITM and ETM are for the LIGO Input Test Mass and End Test Mass, respectively [7, 8]

2.2 TNC

These measurements are nicely covered in [4], with the exception of the substrate thickness, H , which had to be found in [5]. The silica substrates were 1” in diameter and 1/4” in thickness. The film measured here was an old quarter-wave stack produced by REO, made of silica/tantala. To get the value of $S_x(100\text{Hz})$, I plugged their measured value of $\phi_c = 4.43 \times 10^{-4}$ into their equation (8). Again, this should give an approximation of the coating Brownian noise they would have measured at 100 Hz.

3 The simplest scaling

The easiest approach we can do is to look at how scaling works for half-infinite mirrors. In this case, $S_x \propto d/w^2$ [11]. Therefore, scaling can easily be accomplished by using the following equation:

$$S_x^{\text{pred}} = \frac{d_{\text{pred}}}{d_{\text{meas}}} \left(\frac{w_{\text{meas}}}{w_{\text{pred}}} \right)^2 S_x^{\text{meas}}. \quad (1)$$

Here, S_x^{pred} is what we’re after for either ITM or ETM, and d_{pred} and w_{pred} would be the coating thickness and beam spot size for the relevant optic (ITM or ETM). Similarly, d_{meas} and w_{meas} would be the film thickness and beam spot size for the measured optic (TNI, TNC), and of course, S_x^{meas} would be the directly measured coating Brownian thermal noise.

If we do that, we get the results presented in table 2 and the noise plotted in figure 1.

Optic	$S_{\text{pred}}^{ITM} [\text{m}^2 \text{ Hz}^{-1}]$	$S_{\text{pred}}^{ETM} [\text{m}^2 \text{ Hz}^{-1}]$	$S_{\text{IFO}} [\text{Hz}^{-1}]$
TNI(1)	5.94e-41	9.15e-41	1.89e-47
TNI(2)	4.16e-41	6.41e-41	1.32e-47
TNI(3)	4.72e-41	7.27e-41	1.50e-47
TNI(4)	4.58e-41	7.05e-41	1.45e-47
TNC	8.02e-41	1.23e-41	2.55e-47

Table 2: Calculated values of $S_x(100\text{Hz})$ for End Test Masses (ETM) and Input Test Masses (ITM), as predicted by scaling the measured noises for each experiment the simple scaling formula in equation 1.

4 More Complicated Scaling

I think we need to apply two scaling rules, first for the beam-spot and substrate size, and then for the film thickness. For the beam-spot and substrate dependence, we rely on the work by Somiya and Yamamoto [9]. In that paper, they calculate the Brownian noise of a coating on a finite-sized substrate, which we can write as:

$$S_x^{\text{FIN}}(\Omega) = \frac{8k_B T}{\Omega} \Phi_c U^{\text{FIN}} \quad (2)$$

(from their equation (3)). Here, $S_x^{\text{FIN}}(\Omega)$ is the coating Brownian noise for a finite size mirror at frequency Ω , k_B is Boltzmann's constant, T is the temperature of the optic, Φ_c is the mechanical loss of the coating material, and U^{FIN} is the energy stored in the film from an imaginary force used to probe the fluctuations (in the shape of the beam intensity). We can then take the ratio of this value to that of a coating with the same properties on an infinite substrate $S_x^{\text{INF}}(\Omega)$:

$$R = \frac{S_x^{\text{FIN}}(\Omega)}{S_x^{\text{INF}}(\Omega)}, \quad (3)$$

where $S_x^{\text{INF}}(\Omega)$ is given by their equation (29):

$$S_x^{\text{INF}}(\Omega) = \frac{4k_B T}{\Omega} \frac{d}{\pi w_0^2} \Phi_c \frac{Y_c^2(1 + \nu_s)^2(1 - 2\nu_s)^2 + Y_s^2(1 + \nu_c)^2(1 - 2\nu_c)}{Y_s^2 Y_c (1 - \nu_c^2)}. \quad (4)$$

Here, Y is the Young's modulus and ν is the Poisson ratio, subscripts c and s indicate properties of the coating and substrate, respectively, and d indicates the film thickness. Combining equations 2, 3, and 4, we come to the relation:

$$R = 2U^{\text{FIN}} \frac{\pi w_0^2}{d} \left[\frac{Y_c^2(1 + \nu_s)^2(1 - 2\nu_s)^2 + Y_s^2(1 + \nu_c)^2(1 - 2\nu_c)}{Y_s^2 Y_c (1 - \nu_c^2)} \right]^{-1}. \quad (5)$$

The attached Mathematica notebook is written to calculate this ratio using the equations in [9], but for some reason, it isn't giving reasonable values

Once we are able to calculate R , we should make them for each of the laboratory measurements, as well as for the ITM and ETM mirrors, but assuming




Figure 1: Most recent public sensitivity curve for L1 compared to scaled sensitivity of direct thermal noise measurements using the simple scaling relation in equation 1.

the same thickness as the laboratory measurements. For example, we can calculate $R_{\text{TNI}(1)}$, the ratio of the TNI(1) measurement to its imaginary infinite substrate case, and $R_{\text{ITM}}(d = d_{\text{TNI}(1)})$, which will be the same ratio for the noise we expect from the ITM mirror if it had a coating the same thickness as the TNI(1) measurement. Then we have the following:

$$R_{\text{TNI}(1)} = \frac{S_{\text{TNI}(1)}^{\text{measured}}}{S_{\text{INF}}(d = d_{\text{TNI}(1)})} \quad (6)$$

$$R_{\text{ITM}}(d = d_{\text{TNI}(1)}) = \frac{S_{\text{ITM}}^{\text{predicted}}(d = d_{\text{TNI}(1)})}{S_{\text{INF}}(d = d_{\text{TNI}(1)})} \quad (7)$$

$$S_{\text{ITM}}^{\text{predicted}}(d = d_{\text{TNI}(1)}) = S_{\text{TNI}(1)}^{\text{measured}} \frac{R_{\text{ITM}}(d = d_{\text{TNI}(1)})}{R_{\text{TNI}(1)}} \quad (8)$$

This line of reasoning only gets us halfway there, as we're really interested in $S_{\text{ITM}}^{\text{predicted}}(d = d_{\text{ITM}})$. This is easy to scale to, since the noise is directly proportional to the coating thickness, as in equation 4. Therefore, we can make the final scaling using the relation:

$$S_{\text{ITM}}^{\text{predicted}} = \frac{d_{\text{ITM}}}{d_{\text{TNI}(1)}} S_{\text{ITM}}^{\text{predicted}}(d = d_{\text{TNI}(1)}), \quad (9)$$

which is exactly the value we are trying to calculate.

Optic	U^{FIN} [J]
TNI	2.37e-8
TNC	2.14e-8
ITM	5.096e-11
ETM	4.056e-11

Table 3: Values useful for converting coating Brownian noise, as calculated using Liu and Thorne [10]. All TNI measurements have the same value because they all used the same substrate size and beam size. TNC value is basically equal to U^{INF} due to the extreme spot size to mirror radius ratio.

Looking back, we can actually skip the calculation of S^{INF} , as it cancels in all of the equations, and the ratio of R s in equation 8 can be replaced with the ratios of U^{FIN} s. We can also combine equation 9 with equation 8 to get a final equation:

$$S_{\text{ITM}}^{\text{predicted}} = \frac{d_{\text{ITM}}}{d_{\text{TNI}(1)}} \frac{U_{\text{ITM}}(d = d_{\text{TNI}(1)})}{U_{\text{TNI}(1)}} S_{\text{TNI}(1)}^{\text{measured}}. \quad (10)$$

5 Cheating, with Liu and Thorne

Since I was having difficulty getting the Somiya [9] calculations to work out (still trying though), Eric Gustafson suggested that I try using Liu and Thorne [10] instead. Liu and Thorne calculate the correction to the thermal noise for a finite-sized substrate. They do not consider coatings at all. However, as both Nakagawa [11] and Levin [12] have shown (for infinite substrates, anyway), the loss of a total coated substrate is:

$$S^{\text{Total}} = S^{\text{Substrate}} \left[1 + \frac{2}{\sqrt{\pi}} \frac{(1 - 2\sigma)}{(1 - \sigma)} \frac{\phi_{\text{coating}}}{\phi_{\text{substrate}}} \left(\frac{d}{w} \right) \right]. \quad (11)$$

So it's not terribly unreasonable to assume that the only correction we need to make is one to $S^{\text{Substrate}}$, since it's going to get carried through anyway.

The further beauty of using Liu and Thorne's calculations is that I can get them to work in Mathematica (barely)¹, and that the energy ratios don't have a film thickness dependence. Running them through the calculations I get the Energy values (U^{FIN}) discussed in equations 2 and 10. These are listed in table 3. If I plug them into equation 10, I get the results in table 4. These might be close representatives to what we would see if we were to place these coatings on aLIGO mirrors and somehow make them the same thickness as those on the ETM and ITM mirrors.

Finally, to turn displacement noise, S_x , for a single mirror into strain noise in the interferometer, we just add the noise for each mirror and divide by the arm length:

$$S_{\text{IFO}} = 2 * (S_x^{\text{ITM}} + S_x^{\text{ETM}}) / L^2, \quad (12)$$

¹I ran the numbers through the GWINC finite substrate correction code and got the same answers

Optic	$S_{\text{pred}}^{\text{ITM}}$ [$\text{m}^2 \text{Hz}^{-1}$]	$S_{\text{pred}}^{\text{ETM}}$ [$\text{m}^2 \text{Hz}^{-1}$]	S_{IFO} [Hz^{-1}]
TNI(1)	1.40e-38	2.35e-38	4.69e-45
TNI(2)	0.98e-38	1.65e-38	3.28e-45
TNI(3)	1.11e-38	1.87e-38	3.73e-45
TNI(4)	1.08e-38	1.81e-38	3.62e-45
TNC	1.62e-38	2.71e-38	5.41e-45

Table 4: Calculated values of $S_x(100\text{Hz})$ for End Test Masses (ETM) and Input Test Masses (ITM), as predicted by scaling the measured noises for each experiment using Liu and Thorne and equation 10.

where S_{IFO} is the total power spectral density from mirror Brownian thermal noise in the interferometer, S_x^{ITM} and S_x^{ETM} are the displacement noise we've calculated for the ITM and ETM, respectively, and L is the 4 km arm length of aLIGO. This gives us the final column of table 4. For comparison, the value of $\sqrt{S_{\text{IFO}}}$ from GWINC is $4.25\text{e-}24 \text{ Hz}^{-1/2}$, or $S_{\text{IFO}} = 1.81\text{e-}47 \text{ Hz}^{-1}$.




Figure 2: Most recent public sensitivity curve for L1 compared to scaled sensitivity of direct thermal noise measurements using the Liu and Thorne scaling relation in equation 10.

5.1 Discussion on Liu and Thorne

As much as I'd like to stop here and add a pretty graph or something, I'm not really happy with using Liu and Thorne for coatings. First of all, Liu

and Thorne is not for coatings, and both Nakagawa and Levin are considering semi-infinite test masses. Only Somiya actually calculates the true effect of finite-sized coating thermal noise. So I will keep trying to get that to work. Additionally, I did try to use the Liu and Thorne correction to calculate the results Somiya get in their paper, and I get nothing like their results. However, my calculations can replicate what Liu and Thorne get in their paper, so I at least know it's not my code's fault that this fails.

Figure 2 seems to indicate that scaling using Liu and Thorne does not work for coatings. I've played with this a lot, and no matter how I try to get around it, I'm still off by a couple orders of magnitude. Until I get the Somiya scaling to work I thin the simple scaling is the most reliable answer.

References

- [1] Maria Principe, Innocenzo M. Pinto, Vincenzo Pierro, Riccardo DeSalvo, Ilaria Taurasi, Akira E. Villar, Eric D. Black, Kenneth G. Libbrecht, Christophe Michel, Nazario Morgado, and Laurent Pinard. Material loss angles from direct measurements of broadband thermal noise. *Phys. Rev. D*, 91:022005, Jan 2015.
- [2] Akira E. Villar, Eric D. Black, Riccardo DeSalvo, Kenneth G. Libbrecht, Christophe Michel, Nazario Morgado, Laurent Pinard, Innocenzo M. Pinto, Vincenzo Pierro, Vincenzo Galdi, Maria Principe, and Ilaria Taurasi. Measurement of thermal noise in multilayer coatings with optimized layer thickness. *Phys. Rev. D*, 81:122001, Jun 2010.
- [3] Eric D. Black, Akira Villar, Kyle Barbary, Adam Bushmaker, Jay Heefner, Seiji Kawamura, Fumiko Kawazoe, Luca Matone, Sharon Meidt, Shanti R. Rao, Kevin Schulz, Michael Zhang, and Kenneth G. Libbrecht. Direct observation of broadband coating thermal noise in a suspended interferometer. *Physics Letters A*, 328(1):1 – 5, 2004.
- [4] Tara Chalermongsak, Frank Seifert, Evan D Hall, Koji Arai, Eric K Gustafson, and Rana X Adhikari. Broadband measurement of coating thermal noise in rigid fabryprot cavities. *Metrologia*, 52(1):17, 2015.
- [5] Tara Chalermongsak. *High fidelity probe and mitigation of mirror thermal fluctuations*. PhD thesis, California Institute of Technology, 2014.
- [6] E. Black. TNI design outline. LIGO DCC:T980052.
- [7] G. Billingsly. personal communication.
- [8] W. Kells G. Billingsley, G. Harry. Core optics components design requirements document. LIGO DCC:T000127.
- [9] Kentaro Somiya and Kazuhiro Yamamoto. Coating thermal noise of a finite-size cylindrical mirror. *Phys. Rev. D*, 79:102004, May 2009.

- [10] YT Liu and KS Thorne. Thermoelastic noise and homogeneous thermal noise in finite sized gravitational-wave test masses. *Physical Review D*, 62:122002, 2000.
- [11] N Nakagawa, AM Gretarsson, EK Gustafson, and MM Fejer. Thermal noise in half-infinite mirrors with nonuniform loss: A slab of excess loss in a half-infinite mirror. *Physical Review D*, 65:102001, 2002.
- [12] Y Levin. Internal thermal noise in the LIGO test masses: A direct approach. *Physical Review D*, 57(2):659–663, 1998.